

Tolerance on nominal width with slit edges for high-carbon steel acc. EN 10140 : 2006-09

More tolerances on thickness on request

Dimensions in Millimeters

Nominal thickness		< 125		≥ 125 < 250		≥ 250 < 600	
over	to	A	B	A	B	A	B
	0,60	± 0,15	± 0,10	± 0,20	± 0,13	± 0,25	± 0,18
0,60	1,50	± 0,20	± 0,13	± 0,25	± 0,18	± 0,30	± 0,20
1,50	2,50	± 0,25	± 0,18	± 0,30	± 0,20	± 0,35	± 0,25
2,50	4,00	± 0,30	± 0,20	± 0,35	± 0,25	± 0,40	± 0,30
4,00	6,00	± 0,35	± 0,25	± 0,40	± 0,30	± 0,45	± 0,35

Note: The tolerances on the nominal width for high-carbon steel in hardened condition need to be agreed individually.